

Standard Type List of Quality Specifications

Classification	Product	Viscosity 4%,20°C (mPa·s)	Degree of hydrolysis (mol%)	Remarks
Fully Hydrolyzed Type	V	25.0–31.0	99.3 or higher	
	VC-10	10.5–12.5	99.3 or higher	
	VC-13	13.0–16.0	99.0 or higher	
	VC-20	35.0–45.0	98.5–99.5	
	VF-17	28.0–32.0	98.0–99.0	
	VF-20	35.0–45.0	97.7–98.5	
Medium Hydrolyzed Type	VM-17	25.5–29.5	95.0–97.0	
	VT-13KY	14.5–18.5	92.5–94.5	
Partially Hydrolyzed Type	VP-18	23.0–27.0	86.0–90.0	
	VP-20	30.0–34.0	86.0–90.0	

•pH value in 4% solution: 5–7 (at 20°C).

•The quality specification of J POVAL is based on JIS K 6726 (Test Method to Polyvinyl)

Product Name Explanation

